# **BÖHLER FOX CN 29/9-A**



Stick electrode, high-alloyed, austenitic stainless, special applications

## Classifications

**EN ISO 3581-A**E 29 9 R 3 2 **AWS A5.4 / SFA-5.4**E 39 9 R 3 2

E 312-17

## Characteristics and typical fields of application

Rutile coated, core wire alloyed electrode of E 29 9 R / E312-17 type. Highly alloyed electrode with high ferrite content to offer high tensile strength and excellent resistance to cracking. Primarily intended for dissimilar welding between stainless steel, high strength steel, tool steel; spring steel and 14Mn-steel as well as other difficult-to-weld combinations. The weld metal work hardens making it suitable for wear resisting build-ups on clutches, gear wheels, shafts, etc. Also suitable for repair and maintenance; for instance welding of tools. Designed for first class weld seems and easy handling on AC or DC+. Very good corrosion resistance in wet sulfuric environments, such as in sulfate digesters used by the pulp & paper industry.

## **Base materials**

For steels with higher strength and difficult welding characteristics, joining of dissimilar materials, tool steels, heat treatable or quenched and tempered steels, spring steels, high carbon steels etc.

1.4339 GX32CrNi28-10, 1.4347 GX8CrCrNiN26-7, 1.4340 GX49CrNi27-4, 1.4460 X3CrNiMoN27-5-2

## Typical analysis of all-weld metal

					Ni
wt%	0.11	0.9	0.7	28.8	9.5

# Mechanical properties of all-weld metal - typical values (min. values)

Condition	Yield strength R <sub>p0.2</sub>	Tensile strength R <sub>m</sub>	Elongation A (L <sub>0</sub> =5d <sub>0</sub> )	Impact values ISO-V KV J
	MPa	MPa	%	20°C
II	650 (> 450)	790 (> 660)	24 (> 15)	30

u untreated, as-welded

## Operating data



Polarity	DC+ / AC
Electrode identification	FOX CN 29/9-A E 29 9 R

Dimension mm	Current A
$2.5 \times 300$	60 - 80
$3.2 \times 350$	80 - 110
$4.0 \times 350$	110 – 140
$5.0 \times 450$	140 - 180

Recommended heat input max. 2.0 kJ/mm and interpass temperature max. 150°C.

Preheating and interpass temperature as required by the base metal.

Redrying at 250 - 300°C for min. 2 h if necessary.

# **Approvals**

DB (30.014.16, 20.014.07), CE