

Easy-flo™

Aluminium Bronze Grade Flux Paste



Easy-flo™ Aluminium Bronze Grade Flux Paste

Easy-flo™ Aluminium Bronze Grade Flux Paste is specially formulated for use with silver brazing filler metals on aluminium bronze and other copper alloys containing more than 2% aluminium, but less than 10% aluminium. It is able to dissolve aluminium oxide where other fluxes would fail. It has a working range of 550-775°C and is recommended for use with alloys melting below 725°C (such as several of the Silver-flo™ and Easy-flo™ filler metals).

Conforms to: EN 1045: FH11
Working range: 550-775°C

Directions for Use

Before use stir flux paste well to ensure a consistent mixture throughout. Flux paste should be brushed onto the joint surfaces before assembly. Further flux should then be applied externally either side of the joint mouth.

It is good practice to mechanically clean and degrease the joint surface before applying flux. Heat slowly and evenly to the brazing temperature, without local overheating. Use the flux as a temperature guide - it will become clear or opaque as brazing temperature is approached. If blackening of the flux occurs this is often a sign of insufficient flux, overheating or flux exhaustion.

Flux Residue Removal

The flux residues of this product, left after completion of the brazing operation, are corrosive and should be removed. They can be readily removed by soaking in hot water at a temperature >40°C for between 15 and 30 minutes. Any remaining residues can then be brushed off in running water.

Product Availability

1kg Plastic Pots

Easy-flo™ and Silver-flo™ are Johnson Matthey trademarks and are registered to JM in the EU and certain other countries.

Johnson Matthey Plc cannot anticipate all conditions under which this information and our products or the products of other manufacturers in combination with our products will be used. This information relates only to the specific material designated and may not be valid for such material used in combination with any other materials or in any process. Such information is given in good faith, being based on the latest information available to Johnson Matthey Plc and is, to the best of Johnson Matthey Plc's knowledge and belief, accurate and reliable at the time of preparation. However, no representation, warranty or guarantee is made as to the accuracy or completeness of the information and Johnson Matthey Plc assumes no responsibility therefore and disclaims any liability for any loss, damage or injury howsoever arising (including in respect of any claim brought by any third party) incurred using this information. The product is supplied on the condition that the user accepts responsibility to satisfy himself as to the suitability and completeness of such information for his own particular use. Freedom from patent or any other proprietary rights of any third party must not be assumed. The text and images on this document are Copyright and property of Johnson Matthey.

This datasheet may only be reproduced as information, for use with or for resale of Johnson Matthey products. The JM logo®, Johnson Matthey name® and product names referred to in this document are trademarks of Johnson Matthey. Easy-flo® and Silver-flo® are registered to JM in the EU. Sil-fos™ is registered to JM in the UK and certain other countries but is marketed as Mattiphos™ in Germany and the USA.



Johnson Matthey

Metal Joining York Way, Royston, Hertfordshire, SG8 5HJ, UK

Telephone: +44 (0) 1763 253200

Fax: +44 (0) 1763 253168

email: mj@matthey.com

[www: jm-metaljoining.com](http://www.jm-metaljoining.com)