

## Classifications

EN ISO 18274	AWS A5.14	Material-No.
S Ni 6082 (NiCr20Mn3Nb)	ER NiCr-3	2.4806

## Characteristics and field of use

UTP A 068 HH is predominantly used for joining identical or similar high heat resistant Ni-base alloys, heat resistant austenites, and for joining heat resistant austenitic-ferritic materials such as

2.4816	NiCr15Fe	UNS N06600
2.4817	LC- NiCr15Fe	UNS N10665
1.4876	X10 NiCrAlTi 32 20	UNS N08800
1.6907	X3 CrNiN 18 10	

Also used for joinings of high C content 25/35 CrNi cast steel to 1.4859 or 1.4876 for petrochemical installations with service temperatures up to 900° C.

The welding deposit is hot cracking resistant and does not tend to embrittlement.

## Typical analysis in %

C	Si	Mn	Cr	Ni	Nb	Fe
< 0,02	< 0,2	3,0	20,0	balance	2,7	0,8

## Mechanical properties of the weld metal

Yield strength $R_{P0,2}$	Tensile strength $R_m$	Elongation A	Impact strength $K_V$	
MPa	MPa	%	J [RT]	-196° C
> 380	> 640	> 35	160	80

## Welding instruction

Clean weld area thoroughly. Keep heat input as low as possible and interpass temperature at approx. 150° C.

## Approvals

TÜV (No. 00883), KTA, ABS, GL, DNV

Rod diameter x length [mm]	Current type	Shielding gas (EN ISO 14175)	
1,6 x 1000	DC (-)	I 1	R 1
2,0 x 1000	DC (-)	I 1	R 1
2,4 x 1000	DC (-)	I 1	R 1
3,2 x 1000	DC (-)	I 1	R 1